

# Novo Route LP 64 S2

Last update: - 24 / 06 / 2021 (2)

# High quality – semi gloss One Component Traffic & road marking.

## DEFINITION

**Novo Route LP64 S2** is ready to apply as a road marking. One component based on selective synthetic acrylic resin, pigment and high selective fillers to give good results to be used for long lasting road marking.

# USES

Novo Route LP 64 S2 is used for

- Marking asphalt and concrete flooring of roads.
- High ways, garages, parking and loading areas

### ADVANTAGES

Novo Route LP64 S2 is

- Fast drying.
- Highly abrasion resistance.
- Good weather resistant.

# PROPERTIES @ 25 C°

DESCRIPTION	RESULT
Color	white, black, yellow, red
Glossy	Semi-gloss
Solid of pigment by wt.	(37±2) %
Total Solid by wt.	(57 ±2) %
Total Solid by vol.	(30 ±2) %
Density	$1.40 \pm 0.03$ gm. /cm $^{3}$
Viscosity	90 ± 5 Ku
Surface dry	20 Min
Hard dry	1 hr.
Suggested D.F.T	150 – 300 Micron
Thinner	Novo Sol 13 Or Novo Sol X2
Rate of use	2-3 M <sup>2</sup> /kg/100 μ DFT
	(Depends on surface state)
Shelf life	12 months in suitable storage conditions

#### **NOVOCHEM S.AE**

المقر الرئيس والمصنع

مصر — الجيزة — مدينة السادس من أكتوبر — المنطقة الصناعية الثالثة — بلوك 91،102،103

**Headquarters and Factory** 

Egypt - Giza- 6th of October City - 3rd Industrial Zone - Blocks 91,102,103

# DIRECTION FOR USE

- The surface should be free from dust, oil, and loose particles.
- Apply one or more coat from Novo Route LP
  64 S2, by using brush, roller, or spray
- Use Novo Sol X 2 or Novo Sol 13 as thinner and to clean the tools after application. (5-10)%

# REFLECTIVE PROPERTIES

- Highly Night Vision
- We deliver the most advanced technology of Glass beads with our road marking coat. Our "Echo Star" grade of glass beads has a unique Crystal-clear glass with very spherical shapes "Echo star" glass beads have properties like:
- Double coating adherent.
- Double float adherent.
- Higher refractive index.

## STORAGE

One year under suitable storage conditions. (10-25) C°

# **PRECAUTIONS**

- Keep away from sources of agitation.
- No smoking during work.
- Good ventilations in case of spray applying.
- For skin contact, remove it with suitable cream followed by soap and water cleaning.
- For eye contact, rinse with plenty clean water then ask for medical advice.



Tel.: (+202) 369 182 33 Fax: (+202) 369 182 32









FP-14-07/EN







